

# LORD® 7542 Urethane Adhesive

## Technical Data Sheet

LORD® 7542 adhesive is an equal-mix, two-component urethane adhesive system used to bond FRP, SMC and other plastics with little surface preparation. This adhesive will also bond primed metals. LORD 7542 adhesive system is available in a range of working times to accommodate a wide variety of process requirements.

### Features and Benefits:

**Non-Flammable** – does not require explosion-proof equipment.

**Environmentally Recommended** – does not contain ozone depleting chemicals.

**Environmentally Resistant** – resists weathering, humidity and salt spray.

**Chemically Resistant** – solvent resistant when cured. Painting and most cleaning processes do not affect bond strength.

**UL Approved** – UL 746C certified.

### Application:

**Surface Preparation** – Surfaces should be free of grease, dirt and other contaminants. For plastics, clean the surface with a dry rag wipe or a rag dampened with solvent. For metals, priming or powder painting is recommended.

**Mixing** – Mix LORD 7542-A resin with the appropriate curative at a 1:1 ratio, by volume. Handheld cartridges will automatically dispense the correct volumetric ratio of each component. Once mixed, the adhesive cures rapidly.

**Applying** – Apply adhesive using handheld cartridges or automatic meter/mix/dispense equipment.

- Handheld Cartridges
  1. Load the cartridge into the applicator gun and remove the end caps.
  2. Level the plungers by expelling a small amount of material to ensure both sides are level.
  3. Attach mixing tip and expel a mixer's length of adhesive.
  4. Apply adhesive to substrate and mate the parts within the working time of the adhesive. Clamp in position until adhesive reaches handling strength.
- Meter/Mix/Dispense Equipment  
Contact your Parker Lord representative if assistance is needed using this equipment.

For optimum adhesion, bondline thickness of LORD 7542 adhesive should be 10-40 mil (254-1016 micron). During use, limit the exposure of LORD 7542 adhesive containers to cold temperatures.

**Curing** – LORD 7542 adhesive will cure to full strength in 24 hours or less at 75°F (24°C), depending on the curative used.

### Typical Properties\*

	7542-A Resin	7542-B Curative	7542-C Curative	7542-D Curative
Appearance	Dark Brown Liquid	Tan, Black or Green Liquid	Tan Liquid	Tan Liquid
Viscosity, cP @ 77°F (25°C)	1500 - 4500	7000 - 14,000	4000 - 14,000	5000 - 14,000
Density lb/gal (kg/m <sup>3</sup> )	11.45 - 11.75 (1372 - 1408)	10.3 - 10.6 (1234 - 1270)	10.3 - 10.6 (1234 - 1270)	10.3 - 10.6 (1234 - 1270)
Flash Point, °F (°C) Closed Cup	>200 (>93)	>200 (>93)	>200 (>93)	>200 (>93)

\*Data is typical and not to be used for specification purposes.

**Cleanup** – Clean equipment and tools prior to the adhesive cure with organic solvents such as acetone or methyl ethyl ketone (MEK). Do not use alcohol. Once adhesive is cured, heat the adhesive to 300°F (149°C) or above to soften the adhesive. This allows the parts to be separated and the adhesive to be more easily removed. Some success may be achieved with commercial adhesive strippers.

## Shelf Life/Storage:

Shelf life is six months when stored in a clean, dry environment at 65-85°F (18-30°C) in original, unopened container. Excluding LORD 7542-B Black and 7542-C curatives, prolonged exposure to temperatures below 50°F (10°C) during shipping or storage may cause variations in cured properties and/or significant reduction in shelf life.

After opening, protect adhesive from excessive exposure to moisture by installing desiccant cartridges and/or using dry nitrogen as an inert cover.

## Cautionary Information:

Before using this or any Parker Lord product, refer to the Safety Data Sheet (SDS) and label for safe use and handling instructions.

*For industrial/commercial use only.* Must be applied by trained personnel only. Not to be used in household applications. Not for consumer use.

### Typical Properties\*\* of Resin Mixed with Curative

	7542-A/B	7542-A/C	7542-A/D
Mix Ratio by Volume, Resin to Curative	1:1	1:1	1:1
Solids Content by Weight, %	100	100	100
Working Time, minutes @ 75°F (24°C)	4 - 7	11 - 15	20 - 30
Time to Handling Strength, hours @ 75°F (24°C)	1-2	2	3

\*\*Data is typical and not to be used for specification purposes. Given a 1/2 inch (12.7 mm) bead.

### Typical Cured Properties\*

Hardness ASTM D2240, Method A	87
Tensile Strength at Break, psi (MPa) ASTM D882	1767 (12.18)
Elongation, % ASTM D882	102
Young's Modulus, psi (MPa) ASTM D882	12,900 (88.9)
Glass Transition Temperature (T <sub>g</sub> ), °F (°C) ASTM D3418	115 (46)
Coefficient of Linear Thermal Expansion, ppm/°C ASTM E381	
below T <sub>g</sub>	69
above T <sub>g</sub>	162
Moisture Absorption, % ASTM D570	1.65
Poisson's Ratio ASTM D638	0.414

\*Data is typical and not to be used for specification purposes.

**Bond Performance\***

Substrates	SMC	E-coated Steel	CFRP
Lap Shear @ Room Temperature, psi (MPa)	600 (4.10)	2600 (17.90)	3200 (22.1)
Failure Mode	SF	CF/C	FT
Lap Shear @ 180°F (82°C), psi (MPa)	200 (1.38)	1200 (8.27)	890 (6.14)
Failure Mode	–	C	C
Lap Shear @ -30°F (-34°C), psi (MPa)	820 (5.65)	3300 (22.75)	2800 (19.31)
Failure Mode	SF	CF	SF
Lap Shear after 500 hours Salt Spray Exposure, psi (MPa) Tested after 24 hours	700 (4.80)	1200 (8.27)	3244 (22.37)
Failure Mode	SF	–	SF/C
Test after 168 hours Water Immersion @ 150°F (65°C), psi (MPa)	600 (4.10)	–	3086 (21.28)
Failure Mode	SF	–	SF
Test after 500 hours Humidity Exposure, psi (MPa) 100%RH, 165°F (74°C)	640 (4.40)	3300 (22.75)	3221 (21.52)
Failure Mode	SF	–	SF/C

Substrate	Surface Treatment
Sheet Molded Compound (SMC)	IPA Rag Wipe
E-coated Steel	Dry Rag Wipe
Carbon Fiber Reinforced Plastic (CFRP)	80 Grit Scuff

Bonded Parameters	Bond Area	Film Thickness	Cure	Mix Ratio
Composite Lap Shears	1.0"x1.0"	0.030"	24 hr @ RT	1:1 by Volume
Metal Lap Shears	1.0"x0.5"	0.010"	24 hr @ RT	1:1 by Volume

Failure Mode Definition	Abbreviation
Coating Failure	CF
Cohesive Failure	C
Fiber Tear	FT
Sub Failure	SF

\*Data is typical and not to be used for specification purposes.

Values stated in this document represent typical values as not all tests are run on each lot of material produced. For formalized product specifications for specific product end uses, contact the Customer Support Center.

Information provided herein is based upon tests believed to be reliable. In as much as Parker Lord has no control over the manner in which others may use this information, it does not guarantee the results to be obtained. In addition, Parker Lord does not guarantee the performance of the product or the results obtained from the use of the product or this information where the product has been repackaged by any third party, including but not limited to any product end-user. Nor does the company make any express or implied warranty of merchantability or fitness for a particular purpose concerning the effects or results of such use.

**WARNING — USER RESPONSIBILITY. FAILURE OR IMPROPER SELECTION OR IMPROPER USE OF THE PRODUCTS DESCRIBED HEREIN OR RELATED ITEMS CAN CAUSE DEATH, PERSONAL INJURY AND PROPERTY DAMAGE.**

This document and other information from Parker-Hannifin Corporation, its subsidiaries and authorized distributors provide product or system options for further investigation by users having technical expertise.

The user, through its own analysis and testing, is solely responsible for making the final selection of the system and components and assuring that all performance, endurance, maintenance, safety and warning requirements of the application are met. The user must analyze all aspects of the application, follow applicable industry standards, and follow the information concerning the product in the current product catalog and in any other materials provided from Parker or its subsidiaries or authorized distributors.

To the extent that Parker or its subsidiaries or authorized distributors provide component or system options based upon data or specifications provided by the user, the user is responsible for determining that such data and specifications are suitable and sufficient for all applications and reasonably foreseeable uses of the components or systems.